



0086-CPR-595350



Leiths (Scotland) Ltd
Loch-Hills Quarry, Parkhill, Aberdeen. AB21 7AT
Telephone: 01224 774422
Fax: 01224 772444

13

Certificate No. LHCP-B121

BS EN 13108 – 1

Asphalt Concrete for roads and other trafficked areas
B121 AC 14 EME2 bin 15/25 - Loch-Hills Asphalt Plant

General requirements

Temperature of the mixture			140 °C to 200 °C
Grading (passing)		20 mm test sieve	100 %
		14 mm test sieve	99 %
		6,3 mm test sieve	55 %
		4 mm test sieve	40 %
		2 mm test sieve	32 %
		0,250 mm test sieve	14 %
		0,063 mm test sieve	7,5 %
Binder content			5,4 (5,4%)
Void Content – maximum	BS EN 12697 – 31: 2007	Voids at 100 gyrations	6,0 (6,0 %)
Water sensitivity	NFP-98-251-1 (Duriez)	Resistance at 18°C (MPa)	20.3
		Retained strength ratio	0.98
Resistance to permanent deformation	BS EN 12697 – 22: 2003	Large device: proportional rut depth	,5 (7,5 %)
Stiffness Modulus	BS EN 12697 – 26: 2004	ITSM 20°C at 2.5Hz	(5500 MPa)

Leiths (Scotland) Ltd confirms that the asphalt concrete referred to in this certificate complies with the requirements of BS EN 13108 – 1, including Annex ZA

Authorised by:

N. Anderson. Group Technical Director

Date Valid from	01/03/2013
Date Valid to	Currently Valid
Date of Certificate Issue	25 June 2013